

INSTRUCTIONS TO BEND 2361A AND 2361S STALL BARS

DO NOT HEAT the Aluminum Bar.


Heat the Steel Bar to a dull red before bending.

Cut bar to desired length after bending.

Bend radius as shown:



Form A1054
Date 11-98/A



Minimum Bend Radius

2361A Aluminum - 2"

2361S Steel - 1/2"